

AMETEK® PROCESS & ANALYTICAL INSTRUMENTS

MOCON Laboratory

7500 Mendelssohn Ave. N | Minneapolis, MN 55428 | USA

"Package" Water Vapor Transmission Rate Results Report

MOCON Job Number 448331-2

Time's Up DBA H&H Enterprises

Attn: Monique Favreau

6355 Sunset Corp Dr., Las Vegas, NV 89120

Test Conditions:

1 tot Conditionor							
	Test Gas	Water Vapor	Test Temperature	23.0 °C	73.4 °F		
	Test Gas Concentration	100% RH	Carrier Gas	100%	N ₂ , Dry		

PO#: 21304

Test Results:

est Results:					
Sample Identification	Mocon ID	Water Vapor Transmission Rate g / (package·day)	Steady State or Test Duration*		
CHT2 Container	9467.001	0.0667	120 Hours		
C9T2 Container	9467.002	0.0938	120 Hours		
H9T2 Container	9467.003	0.153	Steady State		
W2T2 Container	9467.004	0.00216	Steady State		
F2T2 Container	9467.005	0.00224	Steady State		

Note: Above sample was analyzed on a Permatran-W Water Vapor Permeability Instrument following a modified ASTM F1249 methodology. The modification allows for full packages to be analyzed (trays, bottles...etc.) in place of Film structures. *If Steady State has not been reached, then the transient data point (normally at 120 hours unless additional time has been purchased) will be reported. The results relate only to the specific items tested.

Remarks: None.

This information represents our best judgement based on work done, but the company (MOCON) assumes no liability whatsoever in connection with the use of information or findings contained herein. This report shall not be reproduced except in full without written approval of the company (MOCON). Any deviations from, additions to, or exclusions from the test method shall be noted in the remarks.

End of Report

Page 1 of



MOCON Laboratory

7500 Mendelssohn Ave. N | Minneapolis, MN 55428 | USA

"Package" Water Vapor Transmission Rate Results Report PO#: 21304 MOCON Job Number 448331-2

Date: 1/7/2019

Test Operator: Date: 1719 Authorized by: Date: 1719 Howard Immel, Standard Lab Supervisor

This information represents our best judgement based on work done, but the company (MOCON) assumes no liability whatsoever in connection with the use of information or findings contained herein. This report shall not be reproduced except in full without written approval of the company (MOCON). Any deviations from, additions to, or exclusions from the test method shall be noted in the remarks. **End of Report**



MOCON Laboratory

7500 Mendelssohn Ave. N | Minneapolis, MN 55428 | USA

ASTM E96 Water Vapor Transmission Rate Package Results Report

MOCON Job Number 493873-2

Time's Up DBA H&H Enterprises

Attn: Sherri Hall

1965 E Russell Rd Ste 303, Las Vegas, NV 89119

Test Conditions:

Test Gas	Water Vapor	Test Temperature	23.0°C	73.4°F
Test Gas Concentration	100% RH	"Wet" Cup Method		

PO#: 24791

Test Results:

Sample Identification	Mocon ID	Water Vapor Transmission Rate g/(package∙day)	¹ Steady State or Test Duration	
T4 BioNatura	11753.001	1.38	Steady State	

Note: Above sample was analyzed using ASTM E96 Cup Test Method. The results relate only to the specific items tested.

¹MOCON defines steady state as the slope of the straight line generated from the weight loss/gain data over time Remarks: None.

Sampling: MOCON Sampled per our standard procedure

Date: 4/9/2024

Test Operator: Carrie Skagerberg

Date:

Authorized by

Kris Bednarchúk

This information represents our best judgement based on work done, but the company (MOCON) assumes no liability whatsoever in connection with the use of information or findings contained herein. This report shall not be reproduced except in full without written approval of the company (MOCON). Any deviations from, additions to, or exclusions from the test method shall be noted in the remarks.

End of Report

QMS 702-012-2 Rev B

Page 1 of 1